



SPECIFICATION

(FUJIAN KUNCAI MATERIAL TECHNOLOGY CO. LTD.)

Product Name: Exterior Sterling Silver KC9103-SW

Appearance: An off-white color, free flowing powder with a pearl luster.

Ingredients & Composition	Chemical Name	Specification	CAS No.	CI No.
	Mica	(66 ~ 71)%	12001-26-2	77019
	Titanium Oxide(TiO ₂)	(23 ~ 28)%	13463-67-7	77891
	Tin Oxide (SnO ₂)	(< 1)%	18282-10-5	77861
	Cerium Oxide (Ce ₂ O ₃)	(< 1)%	1345-13-7	77280
	Polymer	(1 ~ 5)%	2530-83-8	-
	-	-	-	-
	Physical Properties	Particle Size Distribution (PSD)	90% within the range (10 ~ 45) μm	
D50		(20.5 ± 1.5) μm		Malvern Mastersizer 3000
Color		as KC STD		Powder Color, Visual
pH (10 % aqueous suspension)		4.0 ~ 9.0		GB 1717
Loss on Ignition (LOI,105°Cx2hr)		≤ 0.5 %		GB 5211.3
Oil absorption value		(60.0 ~ 90.0) g oil / 100 g powder		GB 5211.15
Bulk Density		(20.0 ~ 40.0) g/100cm ³		GB/T 23771
Density		(2.8 ~ 3.4) g/cm ³ (water=1)		GBT 1713

Address:

Haicheng Road, Yuanhong Invest Zone, Fuqing (Fuzhou), Fujian, China. 350314, Tel: +86-591-85581871
www.fjkuncai.com E-mail:xjh@fjkuncai.com

Revision Date: 2021-04-01 Version:2.0