



# SPECIFICATION

( FUJIAN KUNCAI MATERIAL TECHNOLOGY CO. LTD. )

**Product Name:** Exterior Royal Gold Satin KC9323-SW

**Appearance:** A gold color, free flowing powder with a bland luste.

Ingredients & Composition	Chemical Name	Specification	CAS No.	CI No.
	Mica	(43 ~ 51)%	12001-26-2	77019
	Titanium Oxide(TiO <sub>2</sub> )	(21 ~ 26)%	13463-67-7	77891
	Iron(III) Oxide(Fe <sub>2</sub> O <sub>3</sub> )	(21 ~ 26)%	1309-37-1	77491
	Tin Oxide (SnO <sub>2</sub> )	(< 1)%	18282-10-5	77861
	Cerium Oxide (Ce <sub>2</sub> O <sub>3</sub> )	(< 1)%	1345-13-7	77280
	Polymer	(1 ~ 5)%	2530-83-8	-
	-	-	-	-
Physical Properties	Particle Size Distribution (PSD)	90% within the range (5 ~ 25) μm		Malvern Mastersizer 3000
	D50	(11.0 ± 1.5) μm		Malvern Mastersizer 3000
	Color	as KC STD		Powder Color, Visual
	pH (10 % aqueous suspension)	4.0 ~ 9.0		GB 1717
	Loss on Ignition (LOI,105°Cx2hr)	≤ 0.5 %		GB 5211.3
	Oil absorption value	(70.0 ~ 90.0) g oil / 100 g powder		GB 5211.15
	Bulk Density	(20.0 ~ 40.0) g/100cm <sup>3</sup>		GB/T 23771
	Density	(2.8 ~ 3.4) g/cm <sup>3</sup> (water=1)		GBT 1713

**Address:**

Haicheng Road, Yuanhong Invest Zone, Fuqing (Fuzhou), Fujian, China. 350314, Tel: +86-591-85581871  
www.fjkuncai.com E-mail:xjh@fjkuncai.com

Revision Date: 2021-04-01 Version:2.0