



# SPECIFICATION

( FUJIAN KUNCAI MATERIAL TECHNOLOGY CO. LTD. )

**Product Name:** Exterior Pine Green KC98230-SW

**Appearance:** A white, free flowing powder with a pine green reflection color.

Ingredients & Composition	Chemical Name	Specification	CAS No.	CI No.
	Synthetic Fluorophlogopite	(38 ~ 45)%	12003-38-2	-
	Titanium Oxide(TiO <sub>2</sub> )	(50 ~ 57)%	13463-67-7	77891
	Tin Oxide (SnO <sub>2</sub> )	(< 1)%	18282-10-5	77861
	Cerium Oxide (Ce <sub>2</sub> O <sub>3</sub> )	(< 1)%	1345-13-7	77280
	Polymer	(1 ~ 5)%	2530-83-8	-
	-	-	-	-
	Physical Properties	Particle Size Distribution (PSD)	90% within the range (10 ~ 45) μm	
D50		(20.0 ± 2.0) μm		Malvern Mastersizer 3000
Color		as KC STD		Powder Color, Visual
pH (10 % aqueous suspension)		4.0 ~ 9.0		GB 1717
Loss on Ignition (LOI,105°Cx2hr)		≤ 0.5 %		GB 5211.3
Oil absorption value		(60.0 ~ 90.0) g oil / 100 g powder		GB 5211.15
Bulk Density		(40.0 ~ 60.0) g/100cm <sup>3</sup>		GB/T 23771
Density		(2.8 ~ 3.4) g/cm <sup>3</sup> (water=1)		GBT 1713

**Address:**

Haicheng Road, Yuanhong Invest Zone, Fuqing (Fuzhou), Fujian, China. 350314, Tel: +86-591-85581871  
www.fjkuncai.com E-mail:xjh@fjkuncai.com

Revision Date: 2021-04-01 Version:2.0